



Roofix M

PRODUCT DATA

Description

Specifically developed to provide instant waterproofing for leaking roofs, an all-weather product that can be applied even in damp conditions. Roofix M can be used to repair specific areas that are leaking or totally waterproof an entire roof. This product is multi-purpose and can be utilised on a wide variety of problem areas.

A single pack elastomeric acrylic based (non bitumastic) compound, with built in Draylon fibre reinforcement, providing excellent flexibility and durability. Provides exceptional adhesion to virtually any roofing material. Roofix M does not require special primers, and can provide long term protection in excess of 10 years.

Area of use

Exterior: roof areas, gutters, lead flashing, slates, asbestos, cement, metal, asphalt, old roofing felt, bay window and porch areas. Please fully read this datasheet and product label before use.

Substrates

A wide variety of roofing materials

New roofing felts (or similar materials) can be highly porous and friable (because of the green/grey stone flakes on the top) they also contain high levels of bitumen, it is recommended that these types of new surfaces are allowed to weather for a minimum of 6 - 8 months before the application of Roofix M.

Packing

1 litre, 5 litres and 20 litres

Physical Constants

Colours:	Black, White, Grey & Solar Reflective
Finish:	Semi gloss
Volume solids:	48%
Theoretical spreading rate:	1 sq. metre per litre
Flash point:	42°C
Specific gravity:	1.1 kg/litre
Dry to touch:	16 hours (20°C)
Curing time:	2 - 3 days

**The theoretical spreading rate has been calculated for the stated volume solids and dry film thickness. A practical spreading rate will depend on the actual dry film thickness, the nature of the substrate, and the relevant consumption factor. The physical constants are subject to normal manufacturing tolerances.*

Application Details

Application method:	Brush, soft broom, trowel or spreader
Thinner:	White Spirit
Cleaning of tools:	White Spirit

Surface condition

The surface should be stable, firm, dry and free of dust, sand, loose old paint, dirt, grease and oil. Should not be applied in the rain or when rain is likely. Pooled water must be removed before application.

Please refer to the Material Safety Data Sheet for further information.

For additional guidance please contact your local Technical Sales Representative.

Please check colour before use. If using multiple cans please check batch numbers are the same.

SAFETY: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Material Safety Data Sheets and follow all local or national safety regulations.